# Fabrication of New Nanocomposites (PMMA-SPO-PS-TiC) and Studying Their Structural and Electrical Properties for Humidity Sensors

## Bahaa Hussien Rabee, Idrees Oreibi

University of Babylon, College of Education for Pure Sciences, Department of Physics, Iraq

# Article InfoABSTRACTArticle history:Samples have been prepared by adding Titanium carbide nanoparticles to the<br/>Poly (methyl methacrylate) and Ethylene-alpha olefin co-polymer (SPO) and<br/>Polystyrene (PS) with different weight percentages (o, 2, 4, 6 and 8) wt%.<br/>The FTIR analysis, electrical, dielectric, and structural properties have been<br/>studied.The dielectric loss and The dielectric constant decrease with<br/>increasing of Titanium carbide (TiC) nanoparticles. The A.C electrical

### Keywords:

Electrical Ethylene-alpha olefin Nanocomposites Properties Titanium carbide Samples have been prepared by adding Thamum carbide hanoparticles to the Poly (methyl methacrylate) and Ethylene-alpha olefin co-polymer (SPO) and Polystyrene (PS) with different weight percentages (o, 2, 4, 6 and 8) wt%. The FTIR analysis, electrical, dielectric, and structural properties have been studied. The dielectric loss and The dielectric constant decrease with increasing of Titanium carbide (TiC) nanoparticles. The A.C electrical conductivity increases with increasing of Titanium carbide (TiC) concentrations and frequency. The D.C electrical conductivity increases with increasing of Titanium carbide (TiC) concentration and temperature. The Activation energy decreases with increasing of Titanium carbide (TiC) nanoparticles. The Humidity sensor application showed that the electrical resistance of (PMMA-SPO-PS-TiC) nanocomposites decreases with increase the Humidity.

> Copyright © 2018 Institute of Advanced Engineering and Science. All rights reserved.

### Corresponding Author:

Idrees Oreibi, University of Babylon, College of Education for Pure Sciences, Department of Physics, Iraq. Email: idrees114af@gmail.com

### 1. INTRODUCTION

Transition metal carbides are important materials because they possess some desired properties such as thermal stability, corrosion, and wear resistance, electronic, magnetic, and catalytic characteristics. Among them, titanium carbide (TiC), tungsten carbide (WC), and niobium carbide (NbC) are three kinds of important transition metal carbides, which are applied as cutting tools, ceramics, and wear resistance materials. titanium carbide has a good thermal conductivity and high thermal shock resistance, as well as high abrasion resistance. Titanium carbide powders are ofen used for manufacturing cutting tools, aerospace materials, grinding wheels, abrasive-resistant materials, polishing paste, and magnetic recording heads, as well as crucibles for smelting metals. Titanium carbide is commercially produced from the reduction of titania by carbon in a temperature range between1700 C and 2100 C [1]. Poly (methyl methacrylate) (PMMA) is one of the earliest and best known polymers. PMMA was seen as a replacement for glass in a variety of applications and is currently used extensively in glazing applications. The material is one of the hardest polymers, and is rigid, glassclear with glossy finish and good weather resistance. PMMA is naturally transparent and colorless. The transmission for visible light is very high. Polymeric composites of PMMA are known for their importance in technical applications [2]. Polystyrene (PS) is amorphous polymer with bulky side groups. General purposes PS are hard, rigid, and transparent at room temperature and glass like thermoplastic material which can be soften and distort under heat. It is soluble in aromatic hydrocarbon solvents, cyclohexane and chlorinated hydrocarbons [3]. In this study we use Ethylene-alpha olefin copolymer (SPO), this polymer was discovered in 1991. The SPO having monomer units derived from ethylene and monomer units derived from an alpha olefin of 3 to 20 carbon atoms, a density of 906 to 970 kg/m<sup>3</sup>, an

ISSN: 2302-9285

activation energy of flow of 50 to 100 kJ/mol,a molecular weight distribution of 5.5 to 12 [4]. Humidity monitoring is a necessary activity in many industry fields. Measurement of humidity is of great importance in chemical and medical industries such as respiration monitoring. In addition, humidity sensing is essential in civil and aerospace engineering. It is frequently monitored in giant structures such as planes and bridges to control the possible risk of leakage due to corrosion. Furthermore, it affects product quality and the health of workers in the food industry. Therefore, it has been the focus of research for decades and a great variety of humidity sensors; resistive, capacitive, optical and thermal conductivity have been proposed and examined. In a humidity sensor, low response time, high sensitivity, repeatability, reversibility and noise immunity are required [5].

## 2. RESEARCH METHOD

(PMMA-SPO-PS-TiC) nanocomposites have been prepared by adding Titanium carbide nanoparticles to 70% Poly (methyl methacrylate) and 20% Ethylene-alpha olefin co-polymer (SPO) and 10% Polystyrene(PS) in 40 mL of pure benzene, by using magnetic stirrer for 70 min in 1250 °C. The Titanium carbide nanoparticles was add to the mixture by different concentrations (0, 2, 4, 6, and 8) wt%. FTIR spectra were examiend in wavenumber range (500–4000) cm<sup>-1</sup> by FTIR (Bruker company, German origin, type vertex-70). The D.C electrical properties of nanocomposites were measured by by using the Keithley electrometer type 2400 source mater. The dielectric properties of samples examined with frequency range from 100 Hz to  $5 \times 10^6$  Hz by using LCR meter type (HIOKI 3532-50 LCR HI TESTER). The humidity sensor application of (PMMA-SPO-PS-TiC) nanocomposites was investigated. The sample was placed in box and the water vapor was used as a source of humidity. The control network monitored and controlled variations in humidity. The electrical resistance for different humidity range (30–90)% was measured by using the Keithley electrometer type2400 source mater. The D.C electrical conductivity of nanocomposites calculated for a regular body with a section has along the length (*L*), a constant area (*A*) and electrical resistance (*R*) by using the relation [6]:

$$\sigma_{\rm dc} = \frac{1}{\rho} = \frac{L}{R A} \tag{1}$$

The activation energy can be calculated by [7]:

$$\sigma_{\rm dc} = \sigma_{\rm o} \exp(\frac{-E_{act}}{K_B T}) \tag{2}$$

Where  $\sigma$  is electrical conductivity at T temperature,  $\sigma_0$  is electrical conductivity at 0K, KB is Boltzmann constant and Eact is activation energy. The dielectric constant  $\varepsilon$  calculates by [8]:

$$C_{p} = \frac{\varepsilon' \varepsilon_{\circ} A}{d}$$
(3)

Where Cp is capacitance, d is sample thickness, A is surface area the dielectric loss  $\varepsilon^n$  is [9]:

$$\tan \ \delta = \frac{I_{p}}{I_{q}} = \frac{\varepsilon''}{\varepsilon'}$$
(4)

Where tan  $\delta$  is a loss factor. The AC conductivity  $\sigma$  ac calculates by [10]:

$$\sigma_{\rm A,C} = \omega \varepsilon'' \varepsilon_{\rm o} \tag{5}$$

### 3. RESULTS AND ANALYSIS

The FTIR spectra of (PMMA-SPO-PS-TiC) nanocomposites is shown in Figure 1. From the figure it can seen that the broad bands at around (3000) cm<sup>-1</sup> are observed due to –OH groups. The absorbent peak at around (1723) cm<sup>-1</sup> have been attributed to the C=O stretching mode. Asymmetric stretching and scissoring bending vibrations of CH2 group are appeared at around (1434) cm<sup>-1</sup> [11].





BEEI, Vol. 7, No. 4, December 2018 : 538 – 546



(e)

Figure 1. FTIR spectra for (PMMA-SPO-PS-TiC) nanocomposites. (A) Pure blend, (B) 2 wt.% TiC, (C) 4 wt.% TiC, (D) 6 wt.% TiC, (E) 8 wt.% TiC

Figure 2 shows the images of (PMMA-SPO-PS-TiC) nanocomposites films taken at magnification power  $(10\times)$ . When increasing proportions of TiC nanoparticles in the nanocomposites form a continuous network inside the polymers. This network allows charge carriers to pass through polymer [5].

Figure 3 shows the electrical conductivity increase with increasing of TiC nanoparticles due to increase the number of free charge carriers [5]. Figure 4 shows the electrical conductivity increases with increasing of temperature due to increase the charge carriers in the conduction band [12]. Figure 5 shows the relation between Lnos and the inverse absolute temperature for (PMMA-SPO-PS-TiC) nanocomposites. The activation energy calculates by (2). Figure 6 shows By increasing the TiC nanoparticle concentrations, the activation energy decreases for (PMMA-SPO-PS-TiC) nanocomposites due to create a local energy levels in the band gap which act as traps for the charges [13].

In Figure 7 it is clear that the dielectric constant increases with increasing of TiC nanoparticles. This attributed to the formation of a continuous network of TiC nanoparticles inside the nanocomposite [14]. Figure (8) shows the dielectric constant values decrease with increasing applied flied frequency due to decrease the space charge polarization [15].





(d) (e) Figure 2. Photomicrographs (×10) for (PMMA-SPO-PS-TiC) nanocomposites:(a) blend (b) 2 wt.% TiC (c) 4 wt.% TiC (d) 6 wt.% TiC (e) 8 wt.% TiC



Figure 3. Variation of D.C electrical conductivity with (TiC) nanoparticles wt.% concentration for (PMMA-SPO-PS-TiC) nanocomposites at 30°C



Figure 5. Variation of Ln D.C electrical conductivity with inverse absolute temperature for (PMMA-SPO-PS-TiC) nanocomposites



Figure 6. Variation activation energy for D.C electrical conductivity with concentration of TiC nanoparticles wt.% for (PMMA-SPO-PS-TiC) nanocomposites



Figure 7. Variation of dielectric constant with concentration of TiC nanoparticles wt.% at 100 Hz for (PMMA-SPO-PS-TiC) nanocomposites



Figure 8. Variation of the dielectric constant of of (PMMA-SPO-PS-TiC) nanocomposites with frequency

In Figure 9 the dielectric loss increases with increasing of concentration of TiC nanoparticles due to increase the numbers of charge carries [12]. Figure 10 shows the dielectric loss with the frequency of (PMMA-SPO-PS-TiC) nanocomposites at room temperature. It is clear from the figure that dielectric loss decreases with frequency. The larger value of dielectric loss at low frequency could be due to the mobile charges within the polymer backbone [16].





Figure 9. Variation of Dielectric loss with concentration of TiC nanoparticles at 100Hz for (PMMA-SPO-PS-TiC) nanocomposites



Figure 10. Variation of the dielectric loss with frequency for (PMMA-SPO-PS-TiC) nanocomposites

Figure 11 shows the A.C conductivity is increasing with increase the TiC nanoparticles. This increase due to increase the charge carriers, and the A.C conductivity increases considerably with the increase of frequency due to the motion of charge carriers by hopping process and the excitation of charge carriers to upper states in the conduction band [17].



Figure 11. Variation of A.C electrical conductivity with frequency for (PMMA-SPO-PS-TiC) nanocomposites

Figure 12 shows the measured results of the humidity sensor. In this measurement, the temperature kept constant at room temperature. The experimental results showed that the humidity sensor almost had no humidity hysteresis, the resistance of the sensor decreased as humidity increased. It is universally suggested

that protons and hydroxide ions are quickly diffused due to surface collision or self-ionization of water molecules, and this leads to initial separation of (H+, OH-) ions Due to the amphoteric nature of water, and hence auto ionization reaction of water vapour on a surface, a H2O molecule loses nucleus of one of its hydrogen(H+) atoms to become a hydroxide ion (OH). the increase in density of H+ in the nanocomposites leads to decrease the electrical resistance [18].



Figure 12. Variation of electrical resistance with Humidity (RH%) for (PMMA-SPO-PS-TiC) nanocomposites

### 4. CONCLUSIONS

- a. D.C electrical conductivity for (PMMA-SPO-PS-TiC) nanocomposites increases with increasing of temperature and Titanium carbide (TiC) nanoparticles concentration.
- b. Activation energy, The dielectric loss and The dielectric constant of (PMMA-SPO-PS-TiC) nanocomposites decrease with increasing of Titanium carbide (TiC) nanoparticles concentration.
- c. The dielectric loss and The dielectric constant of (PMMA-SPO-PS-TiC) nanocomposites decrease with increasing of frequency.
- d. The A.C electrical conductivity of (PMMA-SPO-PS-TiC) nanocomposites increases with increasing of frequency(F) and concentrations of Titanium carbide (TiC)nanoparticles .
- e. The (PMMA-SPO-PS-TiC) nanocomposites have high sensitivity for Humidity

### REFERENCES

- [1] Hashim A, Hadi Q. Novel of (Niobium Carbide/Polymer Blend) Nanocomposites: Fabrication and Characterization for Pressure Sensor. Sensor Letter. 2017;15:1–3.
- [2] Rabee B, Habeeb M, Hashim A. Preparation of (PS-PMMA-ZnCl2) Composites and Study their Electrical and Optical Properties. International Journal of Science and Research. 2014; 3:2319-7064.
- [3] Alwan T. Refractive Index Dispersion and Optical Properties of Dye Doped Polystyrene Films. Malaysian Polymer Journal. 2010; 5: 204-213.
- [4] Rabee B, Al-Kareem B, Al Shafaay B.Effect addition Al2O3 on the (A.C, D.C) Electrical Properties of Ethylene-Alpha Olefin Copolymer. International Journal of Science and Research. 2017; 6: 2319-7064
- [5] Hashim A,Habeeb M, Hadi A.Synthesis of Novel Polyvinyl Alcohol–Starch-Copper Oxide Nanocomposites for Humidity Sensors Applications with Different Temperatures.Sensor Letter. 2017; 15: 1–4.
- [6] Kadham A, Hassan D, Mohammad N, Hashim A. Fabrication of (Polymer Blend-magnesium Oxide) Nanoparticle and Studying their Optical Properties for Optoelectronic Applications. Bulletin of Electrical Engineering and Informatics (BEEI). 2018; 7(1): 28-34.
- [7] Habeeb M. Effect of Nanosilver Particles on Thermal and Dielectric Properties of (PVA PVP) Films. International Journal of Applied and Natural Sciences. 2013; 2: 103-108.
- [8] Al-Ramadhan Z,Hashim A, and Algidsawi A. The DC Electrical Properties of (PVC-Al2O3) Composites.AIP Conf. Proc: 1400.2011.
- [9] Hashim A, Hadi Q. Structural, electrical and optical properties of (biopolymer blend/titanium carbide) nanocomposites for low cost humidity sensors. Journal of Materials Science Materials in Electronics. 2018; DOI: 10.1007/s10854-018-9257-z.
- [10] Hashima A, Habeeba M, Khalafb A, Hadi A.Synthesis of Novel (Polymer Blend-Titanium Carbide) Nanocomposites and Studying their Characterizations for Piezoelectric Applications. Journal of University of Babylon. 2018; 26(6).
- [11] Habeeb M, Hashim A, Hadi A. Fabrication of New Nanocomposites: CMC-PAA-PbO2 Nanoparticles for Piezoelectric Sensors and Gamma Radiation Shielding Applications. Sensor Letter. 2017; 15: 1–6.

- [12] Zuhair F. The optical and electrical properties of (PVA-PEG-TiO2) (PVA-PEG-Ag) Nanocomposites. M.Sc. Thesis. Iraq: University of Babylon/College of Education for Pure Sciences; 2015.
- [13] Srikanth C, Sridhar B, Prasad M, Mathad R. Characterization and DC Conductivity of Novel CuO Doped Polyvinyl Alcohol (PVA) Nano-Composite Films. Journal of Engineering Researchand Applications. 2014; 4: 38-46.
- [14] AL-humairi M. Study the Optical and Electrical Properties of (PVA-Ag) and (PVA-TiO2) Nanocomposites. M.Sc. thesis. iraq: University of Babylon/College of Education for pure Sciences;2013.
- [15] Habeeb M, Kadhim W. Study of the Electrical Properties of (PVA-PVAC-Ti) Nanocomposites. Australian Journal of Basic and Applied Sciences. 2014; 8: 316-322.
- [16] Hashim A, Agool I, Kadhim K. Novel of (polymer blend-Fe3O4) magnetic nanocomposites: preparation and characterization for thermal energy storage and release, gamma ray shielding, antibacterial activity and humidity sensors applications. Journal of Materials Science Materials in Electronics. 2018; DOI: 10.1007/s10854-018-9095-z.
- [17] Hashim A, Rabee B ,Habeeb M, Abd-alkadhim N, Saad A. Synthesis and Study Electrical Properties of (PS-CaO) Composites. American Journal of Scientific Research. 2012; 75: 5-8.
- [18] Habeeb M, Hamza L. Structural, Optical and D. C Electrical Properties of (PVA-PVP-Y2O3) Films and Their Application for Humidity Sensor. Journal of Advanced Physics. 2017; 6: 1–9.